Product data sheet

BALVER ZINN[®]

		SN100C-StarCore234-E	Rev: 19.10
Date	2023.07.06		
Language	English	1000 C	e-COsol
SDS	950217		Incl. the Made
		BALVERZINN.COM	BALVER ZINN [®]
		SUMMARY	

The REL0 classified, no-clean solder wire StarCore234-E has been specially developed for lead-free repair and rework soldering.

Solder Wire SN100C-StarCore234-E		
PROCESS		
No-Clean process		9
Post-solder cleaning		8
Water soluble		1

INDUSTRY APPLICATION	
Standard electronics	9
Industrial electronics	9
Hi-Rel electronics (automotive)	8

PROCESS CAPABILITY	
Manual soldering	9
Robot soldering	9
Laser soldering	8
Wetting properties	9
Wetting time	9
Solderball formation	8
Flux spattering	9
Smoke formation	8
Tip lifetime	8
Shiny joint appearance	9
Cosmetic cleanliness	8
ICCT compatible	9
Conformal coating	7

CLASSIFICATION	
DIN-EN-ISO-9454-1: 2016	1122
IPC-J-STD-004-A: 2004	ROL0

PROPERTIES		
Flux code	2	34-E
Alloy code	SN	1100C
Alloy composition	SnC	Cu0.7Ni
Liquidus	[°C]	227
Solidus	[°C]	227
Recommended soldering temp.	[°C]	330 - 380
Acid number	[mg KOH/g]	190
Flux content	[% w/w]	2.2
Residues		Colorless

TEST REPORTS			
Certificate of Compliance		Website	
Declaration of Conformity 2011/65/EU (RoHS)			Website
Application Note		EN/DE	
Copper Mirror	IPC-TM-650 2.3.32		Pass
Halides	IPC-TM-650 2.3.33	[Silver Chromate]	-
Halide	IPC-TM-650 2.3.35.1	[Fluoride by Spot]	-
Copper Corrosion	IPC-TM-650 2.6.15		Pass
SIR	IPC-TM-650 2.6.3.3		Pass
ECM	IPC-TM-650 2.6.14.1		Pass

K63

0.4

63

63

11

10

20-25 °C

ΒZ

0.25 / 0.5 / 1.0

80

76 30

10

0.3 - 3.5

60

Legend	
Especially made for this purpose	9 - 10
Generally qualified for this purpose	7 - 8
Generally usable, but not the best choice	5 - 6
Generally not usable for this purpose	3 - 4
Wrong choice	1 - 2

Check material compatibility with every process change!

Industrial chemical product.

Read MSDS before use.

Disclaimer: This information is intended as advice to the best of our knowledge. The provided data is based on our own measurements, they do not provide any guaranteed properties nor are these delivery specifications. Due to the versatility of materials, applications and taking in consideration the industrial property rights of third parties, Balver Zinn Josef Jost GmbH & Co. KG cannot take any liability.

Standard wire diameter [mm]

Minimum shelf-life in months

	PACKAGING AND STORAGE	
9 - 10	Reels	
7 - 8	Label	
5 - 6	Weight [kg]	
3 - 4	Height [mm]	
1 - 2	External diameter [mm]	
	Internal diameter [mm]	
	Reels per carton	